


Technical Product Data Sheet

# ROKU<sup>®</sup> strip



**kuhn**  **odice**

Tech.Rev.: 1.0  
Ling. Rev.: 1.0

## Product description

The ROKU® strip is an expanding, graphite-based fire protection strip. In the event of fire, it forms an insulating foam layer that serves as a barrier against fire and smoke.

The strip is available in different dimensions and can be cut to individual sizes.

Its main applications include joint sealing, cable and pipe penetration seals and door seals in fire protection doors.

## Reaction to fire

- Class E (DIN EN 13501-1)

## Properties

- High expansion rate
- Reliable fire protection
- Flexible and easy to install
- A multitude of applications
- Environmentally friendly

## Fields of application

- Fire protection doors made from wood, steel or aluminium
- Glazing
- Facades
- Safety storage cabinets
- Safes
- Pipe penetration seal systems

## Technical data

|                                           |                                                                                                                                                            |
|-------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Verification                              | ETA-10/0117: 04 October 2016                                                                                                                               |
| Composition                               | Expandable graphite-based foaming material that is free from halogens, asbestos and conflict minerals. Compliant with REACH, RoHS and VOC and UV-resistant |
| Material structure                        | Flexible roll material                                                                                                                                     |
| Volatile components (VOC) [g/l]           | None                                                                                                                                                       |
| Thermal conductivity [W/(m×K)]            | 0.403                                                                                                                                                      |
| Thermal conductivity reference temp. [°C] | 10                                                                                                                                                         |
| Shore A hardness                          | 76.8                                                                                                                                                       |
| Bulk density [kg/m³]                      | 1200 (±10 %)                                                                                                                                               |
| Start of reaction [°C]                    | 190                                                                                                                                                        |
| Expansion rate [x times]                  | 18 – 38                                                                                                                                                    |
| Reference expansion rate                  | 550 °C – 30 min. – with superimposed load                                                                                                                  |
| Intumescent layer                         | Solid, stable material                                                                                                                                     |
| Expansion pressure [N/mm²]                | 0.80 – 1.50                                                                                                                                                |
| Reference expansion pressure              | 300 °C – method 4                                                                                                                                          |
| Direction of expansion                    | Three-dimensional                                                                                                                                          |



## Design variants

ROKU® strip without additional lamination

SK variant: self-adhesive on one side

DF variant: laminated with PVC film in different colours on one side

Other design variants available on request.



## Colour variants

Black, white, red

## Processing information

### 1. Surface preparation:


- The surface to be adhered to must be clean, dry and free from dirt such as dust, grease and oil to ensure optimum adhesion.
- On smooth surfaces, thorough cleaning is particularly important to maximise the adhesive properties of the material.

### 2. Application temperature:

- The recommended application temperature is between +5 °C and +35 °C.

### 3. Application:

- When using the self-adhesive variants (such as the SK variant), remove the protective film just before installation.
- Position the ROKU® strip precisely, as subsequent adjustments may negatively affect adhesion. Apply the material with even pressure to ensure full adhesion.



## Delivery forms

Standard lengths [mm] 25,000 and 50,000

Standard widths [mm] Up to 300

Standard thicknesses [mm] 1.5 and 2.0 (special thicknesses available upon request)

All cuts (length × width) are produced in accordance with the general tolerance DIN ISO 2768-1-c.

All moulded parts and punched parts are produced in accordance with the general tolerance DIN 7715-5-p2.

Contact:

KuhnOdice Germany GmbH

Jägersgrund 10

57339 Erndtebrück

Germany

+49 2753 5945-0

[info@kuhnodice.com](mailto:info@kuhnodice.com)

[kuhnodice.com](http://kuhnodice.com)