

SeaRox® SL 620

SeaRox SL 620 is a semi-rigid stone wool insulation slab (board). Reinforced aluminium foil (ALU) and glass cloth (GW200, GW400, GW-A, ALU-G) facings are available on request.



Application

The slab (board) is suitable for fire-rated A-class constructions of steel and aluminium bulkheads and decks.

Product properties

Product property	Performance										Norms
Thermal conductivity	T (°C) λ (W/mK)	10	50	100	200	300	400	500	600		EN 12667
		0,035	0,039	0,045	0,059	0,079	0,103	0,133	0,168		
Maximum service temperature		660°C									EN 14706
Advised maximum surface temp. for facings		80°C									
Nominal density		100 kg/m³									EN 1602
Fire classification		Non-combustible Approved for A-class constructions Low flame spread properties (for facings)									IMO 2010 FTP Code
Water absorption		≤ 1 kg/m²									EN 1609 EN ISO 29767
Sound absorption (directly mounted)		Thickness: 40 mm unfaced α _w = 0,80 Thickness: 60 mm unfaced α _w = 0,90									ISO 354 (approximated) Evaluated after ISO 11 654

Compliance

- SeaRox SL 620 complies with directive 2014/90/EU of 23 July on marine equipment (MED) and IMO 2010 FTP Code.
- Above product declarations are also applicable for product with optional facing.
- ROCKWOOL stone wool insulation is made from volcanic rock and complies with Note Q, regulation (EC) No. 1272/2008.



0575

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL A/S and cannot be used without a prior written consent.