

Data sheet

Product name:	Technical Mat 70 (Teknisk Filt 70)
Product description:	Flexible mineral wool mat. Also supplied with reinforced aluminium foil on one side.
Max. application temp.:	500°C. Alufoil: 80°C.
Thermal conductivity:	Calculated:

Mean temp. °C	λ W/m·K
10	0,032
50	0,038
100	0,046
150	0,055
200	0,065
250	0,076
300	0,089

Nominal density:	70 kg/m ³
Fire:	Non-combustible
Dimensional tolerances:	Width: ± 3mm Length: ± 6 mm Thickness: ± 3 mm

A/S Rockwool
P.o. box 4215 Nydalen
N-0401 Oslo
Norway
www.rockwool.no